

# Base Oil 8cSt

## Group III

### Specification

PARAMETERS	TEST METHOD	SPECIFICATION VALUE	TYPICAL VALUE
VISCOSITY AT 100 °C, mm <sup>2</sup> /s	ASTM D 445	7,8-8,2	8,05
VISCOSITY AT 40 °C, mm <sup>2</sup> /s	ASTM D 445	-	49
VISCOSITY INDEX	ASTM D 2270	125 min	137
FLASH POINT, OPEN CUP, ° C	ASTM D 92	220 min	255
POUR POINT, ° C	ASTM D 97	-12 max	-12
COLOR	ASTM D 1500	0,5 max	less 0,5
SATURATES, %	ASTM D 2007	99 min	99,8%
SULFUR, ppm	ASTM D 4294	10 max	less 3
DENSITY, kg/m <sup>3</sup> at 15°C	ASTM D 4052	-	845
NOACK, wt%	ASM D 5800	5,0 max	3,50
APPEARANCE	Visual	bright and clear	bright&clear, colorless