

# PAO 10 cSt

## Isoparaffinic Polyalphaolefin

### Specification

PARAMETERS	TEST METHOD	UNITS	TYPICAL
Kinematic viscosity at 100 °C	ASTM D7042 or D445	mm <sup>2</sup> /s	9.64
Density	ASTM D7042	lb/gal	6.968
Pour point °C	ASTM D5950	°C	-5 -72
Flash point °C	ASTM D92	°C	235.3
Fire point °C	ASTM D92	°C	299 (570)
	ASTM D 6	t-C	
Volatility, NOACK	ASTM D5800	Wt. %	3.5
Viscosity index	ASTM D2270	-	111